

INDEURO

CERAMIC



**GLAZED POLISHED
PORCELAIN
TILES
60X60CM**

GLAZED POLISHED PORCELAIN TILES

INDEURG
CERAMIC



Surface: Glossy



INDEURG
CERAMIC

TRAVERTINE GRAY

**GLAZED
POLISHED
PORCELAIN TILES**
60X60CM



WALL GLOSSY FLOOR

Random Face

Surface: Glossy



TRAVERTINE GRAY

GLAZED
POLISHED
PORCELAIN TILES
60X60CM

Random Face

Surface: Glossy



TRAVERTINE GRAY

GLAZED
POLISHED
PORCELAIN TILES
60X60CM

| r. No. | Property | STANDARD AS PER ISO-13006/EN14411 GROUP BIa | INDEURO Value | Test Method |
|--------|--------------------------------|---|-------------------------------|--------------|
| 1 | Deviation in Length | ± 0.6% | ± 0.3% | ISO 10545-2 |
| 2 | Deviation in Thickness | ± 5% | ± 4% | ISO 10545-2 |
| 3 | Straightness of Sides | ± 0.5% | ± 0.1% | ISO 10545-2 |
| 4 | Rectangularity | ± 0.6% | ± 0.1% | ISO 10545-2 |
| 5 | Surface Flatness | ± 0.5% | ± 0.2% | ISO 10545-2 |
| 6 | Surface Quality (%) | A minimum of 95% of the tiles shall be free from visible defects that would impair the appearance of a major area of tile | 98% free from visible defects | ISO 10545-2 |
| 7 | Glossiness | As per Mfrg | Min 90% | Glossmeter |
| 8 | Modulus of Rupture | > 35 N/mm ³ | 40 N/mm ² | ISO 10545-4 |
| 9 | Breaking Strength | > 1300 N | > 2000 N | ISO 10545-4 |
| 10 | Water absorption | < 0.5% | < 0.08% | ISO 10545-3 |
| 11 | Stain Resistance | Stain Proof | Stain Proof | ISO 10545-14 |
| 12 | Chemical Resistance | No Damage | No Damage | ISO 10545-13 |
| 13 | Thermal Expansion | < 9*10 ⁻⁶ | < 6*10 ⁻⁶ | ISO 10545-8 |
| 14 | Moisture Expansion | Nil | Nil | ISO 10545-10 |
| 15 | Thermal Shock Resistance | No Damage | No Damage | ISO 10545-9 |
| 16 | Resistance Of Surface Abrasion | Manufacturer to state abrasion class | PEI class 3 | ISO 10545-7 |

GLAZED POLISHED PORCELAIN TILES

60X60CM

